

SEAMS (Type 6 and type PB[6])

<i>Clause in standard/Test</i>	<i>Standard</i>	<i>U.M.</i>	<i>Notes</i>
4.2.1 - Resistance to penetration by liquids	-	-	must resist breakthrough - apply spray test to whole suit
4.2.2 - Seam strength (*)	EN-ISO 13395-2 + EN 14325	N	6 Classes 1 >30; 2 >50; 3 >75; 4 >125; 5 >300; 6 >500

(*) clause 5.5 of EN 14325 It must meet **at least the requirements of class 1**